

Nonlinear Optical Response from Excitons in Soliton Lattice Systems of Doped Conducting Polymers

Kikuo HARIGAYA*

Physical Science Division, Electrotechnical Laboratory, Umezono 1-1-4, Tsukuba, Ibaraki 305, Japan

(Received February 14, 1997; accepted for publication March 21, 1997)

Exciton effects on conjugated polymers and the resulting optical nonlinearities are investigated in soliton lattice states. We use the Su-Schrieffer-Heeger model with long-range Coulomb interactions for electrons. The third-harmonic generation (THG) at off-resonant frequencies is calculated as functions of the soliton concentration and the chain length of the polymer. The magnitude of the THG with 10 percent doping increases by the factor of about 10^2 from that of the neutral system. The large increase of the order two is common for several Coulomb interaction strengths, and is seen in open systems as well as in periodic systems.

KEYWORDS: excitons, nonlinear optical response, soliton lattice systems, doped conducting polymers, theory

*E-mail address: harigaya@etl.go.jp; URL: <http://www.etl.go.jp/People/harigaya/>.

The doping effects in conjugated polymers and their linear and nonlinear optical responses are fascinating research topics because of their importance in scientific interests as well as in developing technology. In the previous paper,¹⁾ we theoretically considered exciton effects in the soliton lattice states of doped systems. There is one type of exciton in the undoped system with half-filled electronic states,²⁾ where the excited electron (hole) sits at the bottom of the conduction band (top of the valence band), which we called the intercontinuum exciton.¹⁾ In the soliton lattice states of the doped Su-Schrieffer-Heeger (SSH) model for degenerate conjugated polymers,³⁾ there are small energy gaps between the soliton band and the continuum states, i.e., valence and conduction bands. The number of the types of excitons increases, and their presence effects structures of the optical spectra. A new exciton, which we have named the soliton-continuum exciton,¹⁾ appears when the electron-hole excitation is considered between the soliton band and one of the continuum bands.

We are conducting this study to investigate how large optical nonlinearities are obtained when conjugated polymers are doped with electrons or holes up to as much as 10 percent. The SSH model,³⁾ with the long range Coulomb interactions of the Ohno expression,⁴⁾ is solved with the Hartree-Fock (HF) approximation, and the excitation wavefunctions of electron-hole pairs are calculated by the single-excitation configuration-interaction (single-CI) method. We calculated the off-resonant nonlinear susceptibility as a guideline of the magnitude of the nonlinearity. We looked at the characters of the excitations at off-resonances resulting from the single-CI calculations. The third harmonic generation (THG) at the zero frequency, $\chi_{\text{THG}}^{(3)}(0) = \chi^{(3)}(3\omega; \omega, \omega, \omega)|_{\omega=0}$, is considered with changing of the chain length and the soliton concentration. We will demonstrate that the magnitude of the THG at the 10 percent doping increases by the factor of about 10^2 from that of the neutral system.

The periodic systems simulate the reasonably long systems where chain end effects are small. However, all of the polymers are not sufficiently long enough to neglect end effects, and shorter chains are present. The chain ends might have effects on the electronic structures, excitation properties and the resulting nonlinear optical responses of the polymers. In this paper, we discuss how the chain ends effect the large increase of optical nonlinearity, compared with that of the periodic systems. We will demonstrate that the large increase of the THG upon doping is seen in open systems as well as in periodic systems.

We use the SSH hamiltonian³⁾ with the Coulomb interactions,

$$H = H_{\text{SSH}} + H_{\text{int}}. \quad (1)$$

The first term of eq. (1) is,

$$H_{\text{SSH}} = - \sum_{i,\sigma} (t - \alpha y_i) (c_{i,\sigma}^\dagger c_{i+1,\sigma} + \text{h.c.}) + \frac{K}{2} \sum_i y_i^2, \quad (2)$$

where t is the hopping integral of the system without the bond alternation; α is the electron-phonon coupling constant which changes the hopping integral linearly with respect to the bond variable y_i ; the bond variable is assigned to the bond between the i th and $(i+1)$ th sites ($1 \leq i \leq N-1$, N being the system size); $c_{i,\sigma}$ is an annihilation operator of the π -electron at the site i with spin σ ; the sum is taken over i within $1 \leq i \leq N-1$ due to the open boundary conditions; and the last term with the spring constant K is the harmonic energy of the classical spring simulating the σ -bond effects. The second term of eq. (1) is the long-range Coulomb interaction in the form of the Ohno potential:⁴⁾

$$H_{\text{int}} = U \sum_i (c_{i,\uparrow}^\dagger c_{i,\uparrow} - \frac{n_{\text{el}}}{2})(c_{i,\downarrow}^\dagger c_{i,\downarrow} - \frac{n_{\text{el}}}{2}) \\ + \sum_{i \neq j} W(r_{i,j}) (\sum_\sigma c_{i,\sigma}^\dagger c_{i,\sigma} - n_{\text{el}}) (\sum_\tau c_{j,\tau}^\dagger c_{j,\tau} - n_{\text{el}})$$

where n_{el} is the number of π -electrons per site, $r_{i,j}$ is the distance between the i th and j th sites, and

$$W(r) = \frac{1}{\sqrt{(1/U)^2 + (r/aV)^2}} \quad (4)$$

is the Ohno potential. The quantity $W(0) = U$ is the strength of the onsite interaction, V is the strength of the long range part, and a is the mean bond length.

The model is treated by the HF approximation and the single-CI for the Coulomb potential. The bond variables are calculated by the adiabatic approximation. The self-consistent formalism was explained in our previous paper.¹⁾ The electric field of light is parallel to the polymer chain which is along the x -axis. The optical absorption spectra are calculated by the formula

$$\sum_\kappa E_\kappa P(\omega - E_\kappa) \langle g|x|\kappa \rangle \langle \kappa|x|g \rangle, \quad (5)$$

where $P(\omega) = \gamma/[\pi(\omega^2 + \gamma^2)]$ is the Lorentzian distribution (γ is the width), E_κ is the electron-hole excitation energy, $|\kappa\rangle$ is the κ th excitation, and $|g\rangle$ is the ground state.

The THG is calculated with the conventional formula,⁵⁻⁷⁾ which is sometimes called the sum-over-states method. In order to demonstrate the magnitude of the THG, we use the number density of the CH unit, which is taken from *trans*-polyacetylene: $5.24 \times 10^{22} \text{cm}^{-3}$.⁸⁾ We also use $t = 1.8 \text{ eV}$ in order to look at numerical data in the esu unit. We include a small imaginary part η in the denominator, which assumes a lifetime broadening and suppresses the height of the δ -function peaks. The THG at $\omega = 0$ does not sensitively depend on the choice of η . This can be checked by varying the broadening. Here, we report the results with the value $\eta = 0.02t$.

The system size is chosen as $N = 80, 100, 120$ when the electron number is even (it is varied from $N_{\text{el}} = N, N+2, N+4, N+6, N+8, N+10$ to $N+12$). We change Coulomb interaction parameters arbitrarily within a reasonable range in order to look at general properties of the optical nonlinearities of the soliton lattice systems. We take two combinations of the Coulomb parameters $(U, V) = (2t, 1t)$ and $(4t, 2t)$ as representative cases. The other parameters, $t = 1.8 \text{ eV}$, $K = 21 \text{ eV/\AA}^2$ and $\alpha = 4.1$

eV/Å, are fixed in view of the general interests of this study. All the quantities of the energy dimensions are shown in units of t .

Figure 1 shows the typical lattice configuration and excess-electron density distribution of open systems for $N = 100$, $N_{\text{el}} = 102$, $U = 4t$ and $V = 2t$. Both quantities are smoothed by removing small oscillations between even- and odd-number sites. There are two charged solitons due to the excess-electron number $N_{\text{el}} - N = 2$. The two solitons are centered around the 20th and 80th lattice sites. They would be around the 25th and 75th sites in the periodic boundary system. The solitons are moved slightly closer to the chain ends. This is the end effect, due to the enhanced bond-alternation strengths near the 1st and 100th sites. The enhanced bond variables pull the two solitons in the direction of the chain ends. These effects have already been seen in an earlier paper.⁹⁾ The excess-electron density shows that the doped charges accumulate with the maxima at the soliton centers.

Following, we calculate the optical spectra, linear absorption and THG, and consider the exciton effects. Figure 2 (a) shows the typical optical absorption spectrum at the 2 % soliton concentration for $(U, V) = (4t, 2t)$. The broadening $\gamma = 0.05t$ is used. There are two main features around the energies $0.7t$ and $1.4t$. The former originates from the soliton-continuum exciton, and the latter is from the intercontinuum exciton. The presence of the chain ends does not effect the excitation energies so much. However, the oscillator strengths of the soliton-continuum exciton become relatively larger than those in the periodic system. This is a new property which is found in the system with open boundaries. We have treated the periodic system with ring geometries, and the open system with geometries of linear chains. Thus, the expectation values of dipole operators are generally larger in the open system than in the periodic system. A similar fact has been discussed for the uniformly dimerized system without solitons in ref. 10.

Figure 2 (b) displays the absolute value of the THG against the excitation energy ω . The abscissa is scaled by a factor of 3 so that the features in the THG are located at similar points to those in the abscissa of Fig. 2 (a). The large feature at approximately $\omega = 0.22t$ originates from the lowest excitation of the soliton-continuum exciton and the other feature at approximately $\omega = 0.26t$ originates from the higher excitations. The features from the intercontinuum exciton extend from $\omega = 0.48t$ to the higher energies. The soliton-continuum exciton gives rise to the large optical nonlinearity, as we looked in the linear absorption. The oscillator strengths accumulate at the lowest excited state of the soliton-continuum exciton while the doping proceeds, as we have shown in ref. 1. This feature mainly contributes to the large optical nonlinearity of the doped systems. The THG spectra, such as in Fig. 2 (b), are calculated for the three system sizes, $N = 80, 100, 120$, and for the soliton concentrations up to 10 %, in order to compare to the calculations for the system with periodic boundaries.

Figures 3 (a) and 3 (b) display the variations of the absolute value of $\chi_{\text{THG}}^{(3)}(0)$ for $(U, V) = (2t, 1t)$ and $(4t, 2t)$,

respectively. The plots are the numerical data: the open symbols are for the periodic systems, and the closed symbols are for the present calculations of the systems with chain ends. The dashed lines are guides for the plots of the periodic systems, showing the overall behavior for each system size. The finite system size effects¹¹⁾ appear in these figures. It is known that the THG is not size consistent, and spectral shapes depend on the system size when N is as large as 100.¹¹⁾ This fact is reflected in the separation of the plots of the three system sizes with periodic and open boundaries.

The off-resonant THG near zero concentration increases very rapidly, but the THG still increases for a few percent up to a 10 % soliton concentration. The increase between the zero concentration and the 10 % concentration is by the factor of approximately 100. This behavior is consistent for the two boundary conditions and the Coulomb interaction parameters. The main difference between the two boundary conditions is that the THG with open boundaries is larger than that of the periodic system, when the concentration, system size, and the Coulomb parameters are the same. A similar property has been discussed in the calculations of the half-filled systems.¹⁰⁾

When we look at the enhancement factor in detail, it is discovered that the enhancement is particularly large for the open boundary systems with two solitons. This is seen for the three closed symbols near 2 % concentration in Figs. 3 (a) and 3 (b). These are the cases of the concentrations of 2.5 %, 2.0 %, and 1.67 %, for $N = 80, 100$, and 120, respectively. Therefore, if the limit of the long chain is taken, there is a jump of the THG between the zero concentration and the infinitesimal concentration. This is different from the expected smooth behaviors of the periodic chains. The presence of the chain ends results in the trapping of solitons near the ends, and thus the THG jumps suddenly at the zero concentration limit.

The dramatic enhancement of the THG in the case of two solitons is clear when we consider the ratio of the THG value of the open system with respect to that of the periodic system. The calculations have been done for $(U, V) = (4t, 2t)$, and the ratio is shown in Fig. 4. The numerical data are shown by the triangles ($N = 80$), circles ($N = 100$), and squares ($N = 120$). Except for the three plots near the concentration of 2 %, the ratio is constant at approximately 3. It becomes greater than 10 for the two soliton systems. Thus, we have found that the case with two solitons is special, mainly due to the chain end effects. It should be noted that the large THG due to the presence of chain ends could be used as a tool for increasing nonlinear optical responses experimentally. The reason for the large enhancement can be understood as follows. In two soliton solutions with the open boundary condition, the intersoliton distance becomes longer than in the system with periodic boundaries. This gives rise to the larger expectation values of the dipole moment operators, and thus we obtain the greatly enhanced THG in the system with two solitons.

In summary, we have considered the off-resonant nonlinear susceptibility as a guideline of the strength of the nonlinearity in the doped conjugated polymers. We have

calculated the off-resonant THG with various system sizes and the soliton concentration for the chains with open boundaries. We have shown that the magnitude of the THG at 10 percent doping increases by the factor of 10^2 from that of the neutral system. The large increase of the order two is common for several Coulomb interaction strengths, and is seen in the open systems as well as in the periodic systems.

Acknowledgments

The author acknowledges valuable discussions with Professor T. Kobayashi, Professor S. Stafström, Dr. S. Abe, Dr. Y. Shimoï, and Dr. A. Takahashi.

References

- 1) K. Harigaya, Y. Shimoi and S. Abe: J. Phys.: Condens. Matter **7** (1995) 4061.
- 2) S. Abe, J. Yu and W. P. Su: Phys. Rev. B **45** (1992) 8264.
- 3) W. P. Su, J. R. Schrieffer and A. J. Heeger: Phys. Rev. B **22** (1980) 2099.
- 4) K. Ohno: Theor. Chim. Acta **2** (1964) 219.
- 5) N. Bloembergen: *Nonlinear Optics* (Benjamin, New York, 1965).
- 6) B. J. Orr and J. F. Ward: Mol. Phys. **20** (1971) 513.
- 7) J. Yu, B. Friedman, P. R. Baldwin and W. P. Su: Phys. Rev. B **39** (1989) 12814.
- 8) C. R. Fincher, C. E. Chen, A. J. Heeger, A. G. MacDiarmid and J. B. Hastings: Phys. Rev. Lett. **48** (1982) 100.
- 9) S. Stafström and K. A. Chao: Phys. Rev. B **30** (1984) 2098.
- 10) S. Abe, M. Schreiber and W. P. Su: Chem. Phys. Lett. **192** (1992) 425.
- 11) S. Abe, M. Schreiber, W. P. Su and J. Yu: J. Lumin. **53** (1992) 519.

Figure captions

Fig. 1. (a) The bond alternation order parameter, $(-1)^n(y_{n+1}-y_n)/2$, and (b) the excess-electron density, $(\rho_{n-1}+2\rho_n+\rho_{n+1})/4$. The parameters are $U = 4t$, $V = 2t$, $N = 100$, and $N_{\text{el}} = 102$. See the text for the other parameters.

Fig. 2. (a) The optical absorption spectrum and (b) the absolute value of the THG, for the open system with the size $N = 100$, the electron number $N_{\text{el}} = 102$, and $(U, V) = (4t, 2t)$. The broadening $\gamma = 0.05t$ is used in (a), and $\eta = 0.02t$ is used in (b). The absorption is shown in arbitrary units, and the nonlinear optical response is in esu units.

Fig. 3. The absolute value of the THG at $\omega = 0$ v.s. the soliton concentration for (a) $(U, V) = (2t, 1t)$ and (b) $(4t, 2t)$. The numerical data are shown by the triangles ($N = 80$), circles ($N = 100$), and squares ($N = 120$). The data of the system with the periodic boundary condition are shown by the open symbols. And, the data with the open boundaries are shown by the closed symbols. The dashed lines are guides.

Fig. 4. The ratio of the absolute values of the THG between the open and periodic boundary conditions, shown against the soliton concentration. The Coulomb parameters are $(U, V) = (4t, 2t)$. The numerical data are shown by the triangles ($N = 80$), circles ($N = 100$), and squares ($N = 120$).